



RX 1 RUST CONVERTER

Anti Oxidization Coating

Uses

Metal products subjected to rusting or atmospheric corrosion during storage or shipping.

Metal Roofs, Ships, Vehicles.

General

RX 1 is water base, it is usually applied to objects at site which are difficult to sand blast, such as vehicles, trailers, fences, iron railings, sheet metal, and the outside of storage tanks.

It may also be used to restore and preserve iron-based items of historical importance.

Advantages

RX1 reacts with rust to convert it to a stable compound that is resistant to water and bacterial growth.

Treated surfaces can be painted with either water based or oil based paints.

Application

1. Wire brush away loss rust.
2. Can be applied directly or diluted 1 – 2 times depending on the extent of the rust.

Drying Time: 10 to 20 minutes

Re-Coating Interval: 30 minutes

Fully Cure: 24 hours

Best to apply on a dry day, above 8°C.

Coverage

8 m²/ 1 liter.

40 m² / 5 liter.

100 m² / 20 liter.

Technical Data

Colour: White colour liquid.

Viscosity: less than 200

pH Value: 1 to 2 acidic

Film Forming: 15°C minimum

Flash Point: 210°C

Resistance to Water: 3 days

Resistance to Solvent: 3 days

Heat Resistance: 100°C

VOC: less than 3% g/litre.

Shelf Life: 12 months.

Storage

Keep containers tightly sealed away from extreme temperature changes and open flames.

Safe Handling:

Handling the product with care.

Provide adequate ventilation when applied on a large scale. Do not inhale vapor.

Proper gloves & safety goggles & facemask must be worn during handling.

Washed hands thoroughly after used.

Packing

1 litre-bottle,

5 litre-carboy,

20 litre-jerry can,

200 litre-drum.

WARRIOR PTE LTD

Blk 17 Marsiling Industrial Estate Road 1 #01-11 Singapore 739279

Tel: (65) 6364 5100

Fax: (65) 6364 0629

war99@singnet.com.sg

www.warrior.com.sg





RX 1 RUST CONVERTER

Anti Oxidization Coating

•

Disclaimer: *The information provided in this brochure is ensured to be as accurate as possible at the time of inclusion, however there may be inadvertent and occasional errors which may have slipped from our notice. Warrior Pte Ltd does not guarantee and make no representations or warranties of any kind about the information, advice and opinions provided and reserves the right to make changes and corrections at any time, without prior notice to any parties. Warrior Pte Ltd accepts no liability for any inaccuracies or omissions in its brochure and any decisions made based on information and opinions contained in the brochure is the sole responsibility of the user*

WARRIOR PTE LTD

Blk 17 Marsiling Industrial Estate Road 1 #01-11 Singapore 739279

Tel: (65) 6364 5100

Fax: (65) 6364 0629

war99@singnet.com.sg

www.warrior.com.sg



CERT NO.: XX-XXXX
ISO 14001: 2004