



FLG80 CHRISTY GLASS

LIQUID CRYSTAL FLOOR HARDENER

USES

1. **Concrete floor hardening** and **dust proofing** of self-levelling screed
2. **Re-waterproofing** of leaky tiled toilet floor by flooding
3. Old flat concrete roof waterproofing
4. **Stop efflorescence** and acid etching on marble

FEATURES

1. **Hardening of Powdery Self-Levelling Cement**
FLG80 is a special silicate compound for the permanent consolidation and hardening of surfaces based on cement materials. Reduces white powdery deposits on the surface of self-levelling cement.
2. **Eliminates or Reduces Efflorescence**
Penetrates the surface and reacts with the free calcium in the concrete or marble, thus hardening, densifying, sealing, dustproofing and reducing water penetration on the stone surfaces. Also reduces or eliminates the formation of efflorescence.
3. **Priming**
Improves the adhesion of subsequently applied paints and coatings to concrete surfaces.
4. **Wear Resistant**
Increases the abrasion, impact and wear resistance of concrete floors where high volumes of pedestrian or forklift traffic are expected.
5. **Stain Resistant**
Reduces the porosity of marble and concrete surfaces to improve the chemical and stain resistance to most organic acids, alkalis, salts and foods.
6. **Breathable Surface**
Treated surface is breathable thus preventing floor sweating.

APPLICATION METHOD

Preferably performed by Professional Waterproofing Contractor

Before treatment, seal and patch all cracks to prevent FLG80 from staining equipment.

For Toilet Waterproofing

Dilute FLG 80 + Water = 1 + 5 to 10 by volume before use.

1. Can be applied to both polished or unpolished new or old concrete and self-levelling screed surfaces without leaving any residue on the surface.
2. Apply by flooding the floor for 1 hour to allow it to penetrate deeply.

WARRIOR PTE LTD

Blk 17 Marsiling Industrial Estate Road 1 # 01-11 Singapore 739279

Tel: (65) 6364 5100 , 6364 5060 , 6367 3676

war99@singnet.com.sg www.warrior.com.sg



FLG80 CHRISTY GLASS

LIQUID CRYSTAL FLOOR HARDENER

APPLICATION METHOD

For Concrete Floors

Dilute **FLG 80 + Water = 1 + 20** before use.


1. Can be applied to both polished or unpolished new or old concrete and self-levelling screed.
2. Apply by brush or rubber spreader.
3. Apply 2 coats and keep it wet for at least 30 minutes to allow it to penetrate deeply.
4. On the next day, sprinkle water on the surface for the chemicals to react further.

REMARKS

During application, direct exposure to sunlight should be avoided. The temperature of the surface to be treated should be between +5°C and +40°C.



Polished Floor



Self-levelling Screed

TECHNICAL DATA

Appearance:	Clear liquid
Specific Gravity:	1.05 - 1.10
Flash Point:	Non-Flammable
	Low VOC; non-toxic; environmentally friendly
pH Value:	9 - 11
Penetration Depth:	2 - 10 mm
Coverage:	8 m ² / 1 kg

PACKING

1-kg bottle, 5-kg pail, 20-kg pail, 250-kg drum

Disclaimer:

The information provided in this brochure is ensured to be as accurate as possible at the time of inclusion, however there may be inadvertent and occasional errors which may have slipped from our notice. Warrior Pte Ltd does not guarantee and make no representations or warranties of any kind about the information, advice and opinions provided and reserves the right to make changes and corrections at any time, without prior notice to any parties. Warrior Pte Ltd accepts no liability for any inaccuracies or omissions in its brochure and any decisions made based on information and opinions contained in the brochure is the sole responsibility of the user.

WARRIOR PTE LTD

Blk 17 Marsiling Industrial Estate Road 1 # 01-11 Singapore 739279

Tel: (65) 6364 5100, 6364 5060, 6367 3676

war99@singnet.com.sg www.warrior.com.sg





FLG80 CHRISTY GLASS

LIQUID CRYSTAL FLOOR HARDENER

SAFETY AND HEALTH PRECAUTIONS

1. May cause sensitization and burns by skin contact. When handling, rubber gloves, face shield, goggles and suitable protective clothing should be worn.
2. **ORAL EXPOSURE:** In case of ingestion, rinse the mouth with water. Call a physician.
3. **INHALATION EXPOSURE:** In case of inhalation, proceed to an open space. If breathing becomes difficult, call a physician.
4. **DERMAL EXPOSURE:** In case of contact, immediately remove clothing and rinse with copious amounts of water. Call a physician.
5. **EYE EXPOSURE:** In case of contact, immediately rinse with copious amounts of water for at least 15 minutes. Assure adequate rinsing by separating the eyelids. Call a physician.

APPLICATION PRECAUTIONS

1. Do not let FLG80 come in contact with glass, windows, aluminum or stainless steel. Will form hard crystals. When dry, it is very hard to remove them.
2. Crystal formed can only be removed by washing with detergent or polishing.

Polishing wax used for
polishing stainless steel



Powder tool

WARRIOR PTE LTD

Blk 17 Marsiling Industrial Estate Road 1 # 01-11 Singapore 739279

Tel: (65) 6364 5100 , 6364 5060 , 6367 3676

war99@singnet.com.sg www.warrior.com.sg