



CX2 COROCOAT

2-PART, WATER-BASED, ANTI-CORROSION COATING

USES

- Applied on metal or steel decks for ships, yachts & boats
- Excellent for machine parts during storage

FEATURES

- Water-based 2-part system, free from solvent
- Non-flammable, non-toxic and non-hazardous
- Protects against salt, hard use and corrosion
- No primer necessary; Fast drying in less than 20 minutes
- Flexible coating that will absorb movement well
- For use above the water line



APPLICATION METHOD

- Metal parts are to be clean and free from oil.
- Remove oil, grease and other contaminations with a suitable detergent, followed by rinsing with water at high pressure.
- Add zinc dust into the pail of paint and mix thoroughly with a power mixer before use. Use up the content after mixing.
- Apply with a paint brush, roller or spraying machine in 2 coats.

SAFETY PRECAUTIONS

The zinc dust added will generate hydrogen gases that cause the closed container to bulge over time. Exercise caution in releasing the gas to avoid bursting of the container, causing injury.

DRYING AND CURING TIME

- Painting should not be carried out before rain.
- Theoretical Coverage: 300 g/m² @50 microns
- Recommended Dry Film Thickness: 120-150m, 2 to 3 coats
- Dry to the touch: 30 minutes
- Hardening Time: 2 hours
- Full Curing till insoluble in water: 3 hours
- Recoating Intervals: 30 minutes minimum, maximum unlimited



WARRIOR PTE LTD

Blk 17 Marsiling Industrial Estate Road 1 # 01-11 Singapore 739279

Tel: (65) 6364 5100, 6364 5060, 6367 3676

war99@singnet.com.sg www.warrior.com.sg



CX2 COROCOAT

2-PART, WATER-BASED, ANTI-CORROSION COATING

USAGE CONDITIONS

It is recommended to carry out painting in fair weather.

Paint works should not be carried out on damp or rainy days.

- Air temperature: 10 - 40°C
- Relative Humidity: 35 – 75 %
- Surface temperature: 5°C to approximately 40°C.



CLEANING AND MAINTENANCE

1. Immerse the spray gun in clean water during the intervals between spraying to prevent clogging of the nozzle. Rinsing water should be replaced periodically.
2. When painting is completed, the entire set of equipment should be cleaned thoroughly with water and detergent.
3. Extra care should be taken when cleaning the spray gun to prevent clogging of the nozzle.

TECHNICAL DATA

- Toxicity: Free from copper, lead, mercury and tin
- Colours: Grey viscous liquid
- Shelf Life: 6 months



STORAGE

- Store under normal temperature and humidity in sealed condition.
- No special precautions are required against fire.
- If there is long-term exposure to frost during storage, the liquid solution may be separated into 2 phases. The liquid solution should be stirred before use to ensure homogeneity.

PACKING

5-kg pail + 100g Zinc Dust,

20-kg pail + 400g Zinc Dust

Disclaimer:

The information provided in this brochure is ensured to be as accurate as possible at the time of inclusion, however there may be inadvertent and occasional errors which may have slipped from our notice. Warrior Pte Ltd does not guarantee and make no representations or warranties of any kind about the information, advice and opinions provided and reserves the right to make changes and corrections at any time, without prior notice to any parties. Warrior Pte Ltd accepts no liability for any inaccuracies or omissions in its brochure and any decisions made based on information and opinions contained in the brochure is the sole responsibility of the user.

WARRIOR PTE LTD

Blk 17 Marsiling Industrial Estate Road 1 # 01-11 Singapore 739279

Tel: (65) 6364 5100, 6364 5060, 6367 3676

war99@singnet.com.sg www.warrior.com.sg

