



LISTED ON HDB'S LIST OF APPROVED MATERIALS

DPC DAMP PROOF COATING



LIQUID APPLIED ELASTIC MEMBRANE

USES

1. Toilet - As a waterproofing membrane that withstands soaking and movement
2. Tiling - As under-tile waterproofing
3. Roof - As base coat before top coat and expansion joint
4. Window - As a damp proof coating before installing the frame
5. Pool - As a koi pond coating
6. Wall Putty - Added with calcium carbonate powder as external & internal wall putty
7. Basements - Ground level as waterproofing and vapour barrier
8. Silage Storage - To protect concrete from silage attack

FEATURES

1. Single pack, water based, non-toxic, non-hazardous, solvent and plasticizer free
2. Quick drying (touch dry in 1 hour); Dry to form a tough semi-gloss finish
3. Good bonding to various substrates subject to thermal movement; withstands soaking
4. High toughness, flexibility, extensibility and good crack bridging properties
5. Non-staining; Resistant to alkali and silage acids
6. Can be applied onto damp backgrounds

APPLICATION METHOD

1. Newly cast cement needs to be fully cured for 30 days to reduce alkalinity that causes paint blisters.
2. Mix DPC and water at a ratio of 1 : 1.
3. Apply one coat of the mixture as a primer.
4. Allow it to dry before second or third coat of DPC.



3 coats on the roof deck cured into a tacky membrane.

COLOR

Clear, Black, White

PACKING

1 kg, 5 kg, 20 kg

High Performance product



CERT NO.: 2015-0644
ISO 14001 : 2015

WARRIOR PTE LTD

Blk 17 Marsiling Industrial Estate Road 1 # 01-11 Singapore 739279

Tel: (65) 6364 5100

war99@singnet.com.sg www.warrior.com.sg

bizSAFE₃

DPC DAMP PROOF COATING



LIQUID APPLIED ELASTIC MEMBRANE

REMARKS

1. Avoid direct exposure to UV or excessive heat.
2. Water Ponding test should be carried out at least 4 days after all coats have been applied. Under unfavorable drying conditions, this may need to be extended.
3. Do not use it as a top coat; it may be tacky, attracting dirt.

TECHNICAL DATA

Touch-dry: 20 minutes to 1 hour depending on surrounding condition

Elongation: 600%

Coverage:

Metal Surfaces - 50– 60 m² / 20 kg (2 layers with thickness 0.4 - 0.5 mm) or 0.4 kg / m²

Concrete Surfaces - 28 - 35 m² / 20 kg (2 layers with thickness 0.7 - 0.8 mm) or 0.7 kg / m²

DPC TEST REPORT by ELEMENT CONSTRUCTION TESTING(S) PTE LTD DATE: 29 SEPTEMBER 2023

Table (A) - Summary of Test Results

S/N	PROPERTIES / TESTS	*ACCEPTANCE CRITERIA	TEST RESULTS		
1	DIN 1048 Pt 5: 1991 [ADMICE/004: 2010] TESTING CONCRETE - TESTING OF HARDENED CONCRETE (SPECIMENS PREPARED IN MOULD) - WATER PERMEABILITY				
	Resistance to Water Penetration, (mm)	Depth of penetration should be zero	0		
2	ASTM D4541-02 STANDARD TEST METHOD FOR PULL-OFF STRENGTH OF COATINGS USING PORTABLE ADHESION TESTERS				
	Adhesion to Substrate, (N/mm ²)	≥ 0.2 N/mm ²	2.12		
3	ASTM D412-16 (2021) STANDARD TEST METHODS FOR VULCANIZED RUBBER AND THERMOPLASTIC ELASTOMERS - TENSION				
	Tensile Strength, (N/mm ²)	a) Before ageing	≥ 1.2 N/mm ²	3.68	
		b) After ageing at 50°C, 14 days	≥ 1.0 N/mm ² and -ve change ≤ 20%. No limit for +ve change	4.64	
		c) After immersion in the following chemicals for 72 hours at room temperature		i) 0.5% (v/v) NaOCl	3.59
				ii) 1.25% (v/v) NH4OH	3.03
iii) 3.7% (v/v) HCl				3.13	
Elongation at Break, (%)	a) Before ageing	≥ 150%	235		
	b) After ageing at 50°C, 14 days	≥ 120% and -ve change ≤ 20%. No limit for +ve change	197		
	c) After immersion in the following chemicals for 72 hours at room temperature		i) 0.5% (v/v) NaOCl	315	
			ii) 1.25% (v/v) NH4OH	274	
			iii) 3.7% (v/v) HCl	322	
4	ASTM D1640/D1640M-14 (2018) STANDARD TEST METHODS FOR DRYING, CURING, OR FILM FORMATION OF ORGANIC COATINGS				
	Set-to-Touch, (mins)	Should touch dry within 60 mins	55		

Table (A) - Summary of Test Results (Cont.)

S/N	PROPERTIES / TESTS	*ACCEPTANCE CRITERIA	TEST RESULTS
5	ASTM C876/C876M-18 (2022) [ADMICE/001: 2017] STANDARD SPECIFICATION FOR HIGH SOLIDS CONTENT, COLD LIQUID-APPLIED ELASTOMERIC WATERPROOFING MEMBRANE FOR USE WITH SEPARATE WEARING COURSE		
	Crack Bridging	No cracks after 10 cycles of stretching and closing to a width of 1mm	No crack was observed
No cracking at 2mm width		No crack was observed	
6	ASTM D2240-15 (2021) STANDARD TEST METHOD FOR RUBBER PROPERTY - DUROMETER HARDNESS		
	Hardness (Shore A)	≥ 30	86
7	FTIR, DTA & TGA [ADMIC&B/001: 2021 & ADMIC&B/002: 2021] VERIFICATION OF BASE POLYMER & POLYMER CONTENT		
	Verification of Base Polymer	Polymer which undergoes hydrolysis should not be used	Styrene-Butadiene Rubber (SBR) (Does not undergoes hydrolysis)
	Polymer Content, (%)	-	47.43
8	TGA [ADMIC&B/001: 2021] VOLATILE CONTENT		
	Volatile Content, (%)	< 50 %	1.81

Remarks: *Acceptance criteria is based on HDB Product Performance Requirement
- Flexible Non-Cementitious Waterproof Membrane (Water-Based) - New Construction & Ceiling Leakage Repair

Disclaimer:

The information provided in this brochure is ensured to be as accurate as possible at the time of inclusion, however there may be inadvertent and occasional errors which may have slipped from our notice. Warrior Pte Ltd does not guarantee and make no representations or warranties of any kind about the information, advice and opinions provided and reserves the right to make changes and corrections at any time, without prior notice to any parties. Warrior Pte Ltd accepts no liability for any inaccuracies or omissions in its brochure and any decisions made based on information and opinions contained in the brochure is the sole responsibility of the user.

WARRIOR PTE LTD

Blk 17 Marsiling Industrial Estate Road 1 # 01-11 Singapore 739279

Tel: (65) 6364 5100

war99@singnet.com.sg www.warrior.com.sg



CERT NO.: 2015-0644
ISO 14001: 2015

