

E1A + E1BQSC EPOXY

30-MIN QUICK-SET SOLVENT-FREE CLEAR EPOXY

USES

- Self-levelling floor coating
- High solid coating
- Water-resistant tile grout
- · Chemical tank coating
- Pebble adhesive





FEATURES

- A low viscosity epoxy with high adhesive, compressive & tensile strength
- Very clear appearance and none-yellowing; Colour-stable
- Good abrasion with chemical and weathering resistance
- · Adheres to most surfaces with self-levelling characteristics
- Withstands soaking in water

Typical mix ratio: E1 A + E1 BQSC For clear coat = 1.0 kg + 0.5 kgFor color coat = 1.3 kg + 0.5 kg

APPLICATION METHOD

- 1. Ensure surfaces are clean and intact before coating. Using a torch to warm up the damp area will improve adhesion.
- 2. Mix Part B with Part A with a power-mixer for 3 to 5 minutes to ensure complete mixing.
- 3. Reaction between Part A and Part B will generate heat. A greater amount of Part B generates more
- 4. Use the mix when heat can be felt before it starts to gel and thicken in 30 minutes' time.
- 5. Clean tools with soapy water before it hardens.
- 6. E1BQSC curing agent added in lesser quantity will reduce the curing time.
- 7. Reduced dosage of E1BQSC curing agent will improve clarity and hardness of the cured resin.
- 8. · Higher dosage of E 1-BQ Curing Agent will increase flexibility and an opaque finishes.









WARRIOR PTE LTD

Blk 17 Marsiling Industrial Estate Road 1 # 01-11 Singapore 739279

Tel: (65) 6364 5100 , 6364 5060 , 6367 3676

war99@singnet.com.sg www.warrior.com.sg



E1A + E1BQSC EPOXY

30-MIN QUICK-SET SOLVENT-FREE CLEAR EPOXY

TECHNICAL DATA

• Application Method: Roller, Brushes or Airless Spray.

• Pot Life: 30 minutes @30°C

Dry to the Touch: 3 hoursHardening Time: 5 hours

• Full Curing Time: 1 day under room temperature

Tensile Strength: 700 kg / cm²
 Bending Strength: 800 kg / cm²
 Compressive Strength: 1000 kg / cm²

• Elongation: 5.7%

• Colour: Clear transparent, glossy. (Can be tinted accordingly.)

PACKING

For clear coat:

1 set consists of E1A Resin 1 kg

and E1BQSC Hardener 0.5 kg

For grey color coat:

1 set consists of E1A Resin 1.3 kg

and E1BQSC Hardener 0.5 kg

Also available in larger packing sizes.

SAFETY

Curing agent will cause skin irritation. Please apply a barrier cream to reduce skin contact. In case of skin contact, wash with soap and large amount of water for 15 minutes, or seek medical advice as needed.

Disclaimer:

The information provided in this brochure is ensured to be as accurate as possible at the time of inclusion, however there may be inadvertent and occasional errors which may have slipped from our notice. Warrior Pte Ltd does not guarantee and make no representations or warranties of any kind about the information, advice and opinions provided and reserves the right to make changes and corrections at any time, without prior notice to any parties. Warrior Pte Ltd accepts no liability for any inaccuracies or omissions in its brochure and any decisions made based on information and opinions contained in the brochure is the sole responsibility of the user.

WARRIOR PTE LTD