



W1 CEMENT STRENGTHENER



WATERPROOFING THIN SET TILE BONDING, TILE BONDING, NEW TO OLD CONCRETE BONDING, ANTI-CHLORIDE, PLASTICISER, INJECTION POLYMER AND SEALER

FEATURES

Cement added with **W1** will have:

1. **Improved bonding strength by 2 to 3 times** to 30.57 kg/cm². Especially good for bonding metal, glass, homogeneous tiles, granites and marble tiles to prevent staining.
2. **Increased flexural and compressive strength by 40% to 100%**. Compressive strength to 56.00 N/mm². Flexural strength to 10.00 N/mm². (ASTM C 39).
3. **Quicker cement setting time**. Reduced surface cracking and dusting, forming a very tight seal. Good for wall plaster, wet areas and swimming pool waterproofing.
4. **10 to 20 times more resistant to oil, salt water, chloride, acid and vapour penetration**—a feature particularly important in steel-reinforced concrete structures.
5. **Improved plasticity and flow** (ASTM C 124-71). Easier to work with; reduces porosity.
6. **W1 CEMENT STRENGTHENER** is deemed to be suitable for use in contact with potable water tested against SS375 : 2001.

APPLICATION METHOD

Based on Cement: Sand ratio of 1 : 3

1. The amount of water needed is 24% by weight of cement.
2. This can be replaced totally with 24% or less of W1 for optimum performance.

A. For Tile Bonding Aid, Grouting Cement, Vapour Barrier & Waterproofing:

1. Dilute **W1 + Water = 1 + 1** by Volume before adding into the Cement.
2. It will waterproof and bond tiles very strongly onto glass, glazed tile, steel and wood. Fine silica sand of 0.5 mm diameter can be added for grouting tile joints.
3. Add **30% v/v** into grouting cement. Mix well before grouting.

B. For Tile-Over-Tile Bonding:

1. Dilute **W1 + Water = 1 + 1** by Volume before adding into the tile bond cement or cement.
2. Hard brush this slurry onto the existing tile surface with a thickness of about 1.5 mm. While it is still wet, bond on the tile.

Consumption for Floor Screed:

W1 + Water = 1 + 1 by volume

W1 usage = 0.4 kg / m² / 10 mm thick



WARRIOR PTE LTD

Blk 17 Marsiling Industrial Estate Road 1 # 01-11 Singapore 739279

Tel: (65) 6364 5100

war99@singnet.com.sg www.warrior.com.sg

bizSAFE₃



CERT NO.: 2015-0644
ISO 14001 : 2015



W1 CEMENT STRENGTHENER



WATERPROOFING THIN SET TILE BONDING, TILE BONDING, NEW TO OLD CONCRETE BONDING, ANTI-CHLORIDE, PLASTICISER, INJECTION POLYMER AND SEALER

Wall Plaster & Cement Mortar for diverse range of Sealing, Repairs & Waterproofing:

- Wall plastering, spalling concrete, corrosion-preventing prime coat on reinforced steel bar, mending worn out floor and holes, patching works around piping, re-pointing of brick works, tile joints, sealing of old concrete, asbestos sheet, fish tanks & swimming pools.

Coating or Injection into Floor Screed, Wall & Absorbent Surface to Prevent Seepage & Waterproof:

- Use **W1 or Mix W1 + W5 MULTI-BOND**. Dilute as needed to coat, or inject into the brick or cement to seal up porosity. Injection pressure is 100 psi. Normal drying time is 10 days at 30°C.

Type 2 Bonding Method:

To save on W1 consumption and increase bonding strength,

1. Priming Slurry **W1 + Cement = 1 + 2**

- Brush the slurry onto the cement surface while it is still wet. (10 minute drying time)
- Apply the mortar directly onto it.

For Old Concrete and Brick Wall Bonding

1. Priming Slurry **W1 + Water = 1 + 1 or 2**

- Before adding into Portland Cement or Tile Bond Cement at 30% level
- Brush the slurry onto the old concrete surface while it is still wet. (20-minute open time)
- Pour the new concrete mix directly onto it.



W1 used to bond water stopping strip



Re-surfacing of drain using W1



PACKING

1 kg
5 kg
20 kg
200 kg



WARRIOR PTE LTD

Blk 17 Marsiling Industrial Estate Road 1 # 01-11 Singapore 739279

Tel: (65) 6364 5100

war99@singnet.com.sg www.warrior.com.sg

bizSAFE₃



W1 CEMENT STRENGTHENER



WATERPROOFING THIN SET TILE BONDING, TILE BONDING, NEW TO OLD CONCRETE BONDING, ANTI-CHLORIDE, PLASTICISER, INJECTION POLYMER AND SEALER

AWCS TECHNOLOGIES TEST REPORT AWCS/MAT/24/122

DATED 24 APRIL 2024 (ASTM C1042-99, ISO 124:2014)

Curing Conditions

- a) Type I - 14 d in air (23 ± 2) °C, (50 ± 4) % RH
b) Type II - 7 d in air (23 ± 2) °C, (50 ± 4) % RH + 7 d in saturated lime water

Table 1. Summary of Test Results

NO.	PROPERTIES	HDB'S ACCEPTANCE CRITERIA	RESULT	UNIT
1.	Slant Shear Bond Strength (Type I)	≥ 2.8	2.9	N/mm ²
	Slant Shear Bond Strength (Type II)	≥ 8.7	8.8	N/mm ²
2.	Total Solids Content	Determination of solid content value	44.5	%

GREEN LABEL TEST UNDER SGLS CATEGORY 032

DATE: 5 JUNE 2024 REF: CE-8500314384/CHS



Results :

Item No.	Parameter	Test Method	Unit	Result	RPL	SGLS 032 Criteria	Justification
1	Heavy Metals	BCTD/MC/IHM111/2022 Rev (3)					
	• Cadmium (Cd)		%	N.D.	0.01	N.D.	Pass
	• Lead (Pb)		%	N.D.	0.01	N.D.	Pass
	• Total Chromium (Cr)		%	N.D.	0.01	N.D.	Pass
	• Mercury (Hg)		%	N.D.	0.01	N.D.	Pass
2	Volatile Organic Compounds	ISO 11890-2 Ed 3.0 : 2020	g/L	1.19	1.0	25*	Pass
3	Total Halogenated Organic Solvent		%	N.D.	0.01	N.D.	Pass
4	Total Aromatic Organic Solvent		%	N.D.	0.01	N.D.	Pass
5	Epichlorohydrin		%	N.D.	0.01	N.D.	Pass
6	N-Methyl Pyrrolidinone		%	N.D.	0.01	N.D.	Pass
7	Formaldehyde	High Performance Liquid Chromatography	%	N.D.	0.005	N.D.	Pass
8	Alkyl Phenol Ethoxylate	LCMS-MS	%	N.D.	0.005	N.D.	Pass
9	Flash Point	ASTM D3828-16a (2021) (Proc. B)	°C	>61.0	-	>61.0	Pass

Notes : N.D. - Not Detected (< Reporting Limit)

RPL - Reporting Limit

Tests for Formaldehyde, Alkyl Phenol Ethoxylate & Flash Point were performed in conjunction with external laboratory.

SETSCO shall adopt the Simple Acceptance as the decision rule in evaluating conformance to specification.

*Mett, Interior

Disclaimer:

The information provided in this brochure is ensured to be as accurate as possible at the time of inclusion, however there may be inadvertent and occasional errors which may have slipped from our notice. Warrior Pte Ltd does not guarantee and make no representations or warranties of any kind about the information, advice and opinions provided and reserves the right to make changes and corrections at any time, without prior notice to any parties. Warrior Pte Ltd accepts no liability for any inaccuracies or omissions in its brochure and any decisions made based on information and opinions contained in the brochure is the sole responsibility of the user.

WARRIOR PTE LTD

Blk 17 Marsiling Industrial Estate Road 1 # 01-11 Singapore 739279

Tel: (65) 6364 5100

war99@singnet.com.sg www.warrior.com.sg

